

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b>  <b>D04H 1/64</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 96/30576</b>  <b>(43) International Publication Date:</b> 3 October 1996 (03.10.96)
<b>(21) International Application Number:</b> PCT/US96/02639  <b>(22) International Filing Date:</b> 8 March 1996 (08.03.96)  <b>(30) Priority Data:</b> 08/414,540                      31 March 1995 (31.03.95)                      US  <b>(71) Applicant:</b> KIMBERLY-CLARK TISSUE COMPANY [US/US]; 401 North Lake Street, Neenah, WI 54956 (US).  <b>(72) Inventors:</b> RICHARDS, Marc, F.; R.D. 5, Box 132E, Dover, DE 19904 (US). WANG, Kenneth, Y.; 811 General Sterling Drive, West Chester, PA 19382 (US).  <b>(74) Agent:</b> CURTIN, Jeffrey; Kimberly-Clark Corporation, 401 North Lake Street, Neenah, WI 54956 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
<b>(54) Title:</b> PREMOISTENED, FLUSHABLE, DISPOSABLE AND BIODEGRADABLE WET WIPES  <b>(57) Abstract</b>  The present invention provides a pre-moistened, dispersible, and biodegradable wet wipe comprising a web of non-woven fibers contacted with a PVOH containing binder. The binder-contacted web further comprises an aqueous lotion solution comprising from about 0.1 to about 0.9 percent by weight of the lotion of boric acid and from about 5 to about 8 percent by weight of the lotion of an alkali metal bicarbonate. The resulting wet wipe has a pH between 7 and about 9 and a wet strength between about 8 and about 20 oz/in.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

**PREMOISTENED, FLUSHABLE, DISPOSABLE AND BIODEGRADABLE  
WET WIPES**

**FIELD OF THE INVENTION**

This invention relates to personal care,  
5 premoistened, cleansing wet wipes that can be used and  
disposed discreetly and safely by flushing down the toilet  
bowl.

**BACKGROUND OF THE INVENTION**

Pre-moistened, skin cleansing tissues are well  
10 known commercially and are referred to as wet wipes,  
towelettes, and the like. These tissues may be prepared  
from paper or paper products which are treated in such a  
manner so as to improve their wet strength. Such tissues  
are generally sized such that they are useful for use as a  
15 wash cloth, and may be packaged in closed containers.  
Alternatively, the tissues may be individually packaged.

Wet wipe tissues are generally treated with an  
aqueous alcohol solution in order to maintain moistness.  
The tissues may also comprise a surface active detergent,  
20 humectant, and a scenting agent or fragrance.

Numerous wet wipe like materials have been  
described. U.S. Patent 3,808,165 describes a process for  
preparing a wet wipe in which boric acid is added to  
polyvinyl alcohol (PVOH) rather than adding the boric acid  
25 to the lotion at a later time. The web is dried, the heat  
of drying breaking down the organic acids present which  
raises the pH to stabilize the binder. Sodium bicarbonate  
is not used to raise the pH.

U.S. Patent 3,881,210 describes a sanitary wiper comprising a PVOH central layer, wherein the multilayered structure is bonded together by means of embossing roll with a land area of 4 to 25%. However, no stabilizing ingredients, percentages, nor strength criteria are specified.

U.S. Patent 4,309,469 describes a wipe which is bonded with a three part adhesive binder consisting of PVOH and a self-crosslinking thermosetting polymer and a non-self-crosslinking thermosetting polymer. The complexing agent is alpha hydroxy and O-aromatic hydroxy acids rather than boric acid and sodium bicarbonate.

U.S. Patent 4,343,133 describes a polyvinyl acetate latex impregnated towelette, which uses a high percentage of boric acid, at least 3%, which is much too harsh for many applications. This towelette also does not comprise sodium bicarbonate.

U.S. Patent 5,256,417 describes a water dispersible towelette which is impregnated with non-aqueous lotion formulations. The non-aqueous lotion composition of organic compound stabilizes the PVOH binder but does not dissolve PVOH.

U.S. Patent 3,689,314 uses a different process to prepare flushable wrappers for absorbent pads. The PVOH binder and the chemical additives are added together and dried. Heat causes the chemicals to react and render the binder sufficiently strong in the condition of use. The environment of the absorbent pad is a very small zone exposure of low level of saturation of the body fluids. The time of exposure is also limited to a few hours, rather than months. In addition, heating is required for crosslinking after the borax is formed. Furthermore, less than 0.5% sodium bicarbonate is used.

A major concern of many of these existing tissues, which use a flushable binder system containing boric acid, is that boric acid in high dosage can cause toxic skin irritation, particularly in individuals with compromised

skin. Thus, there is a need to provide a gentle lotion system containing low concentrations of boric acid. In addition, all of the wet wipes currently in the marketplace have an acidic pH. The most common range is from a pH of 4.0 to 5.5. The skin's pH is about 5.5 in adults and babies, which is the pH most manufacturers try to achieve when developing pH-balanced products.

U.S. Patent 5,252,332 describes a premoistened, flushable towelette impregnated with polyvinyl alcohol-containing binders. A PVOH based binder is applied to the non-woven web, which is lotionized with a lotion containing boric acid and sodium bicarbonate. The sodium bicarbonate range is stated to be 0.2 to 3%. In addition, the towelette contains an undesirably high quantity of boric acid. The borate to bicarbonate ratio is 4:1 to 1:4, and is preferably 2:1 to 1:2. Moreover, the towelette is susceptible to growth of microorganisms, especially mold, and is therefore not appropriate for long-term storage. In contrast, Applicants' invention provides a borate to bicarbonate ratio of 1:8.5 to 1:12 and provides a far superior wet strength.

Applicants' invention provides a number of features which are desired but not found in the prior art. First, Applicants' invention provides unexpected higher wet strength that are unavailable in other formulations with similar needs. Second, it provides for a high percentage of sodium bicarbonate which enhances cleansing and deodorizing, while providing an alkaline pH suitable for babies and infants. Finally, Applicants' invention is surprisingly compatible with existing Baby Fresh™ lotion system, synergistically making a gentle and efficacious cleansing wipe which is also flushable, dispersible and biodegradable. Applicants' invention provides for the first lotionized wet wipe having an alkaline pH, high wet strength, low boric acid concentrations that provide mildness, and a preservative system providing for long-term storage. Moreover, Applicants' invention surprisingly provides a wet

wipe having an alkaline pH while simultaneously being mild and gentle.

The present invention provides a personal care, pre-moistened, cleansing wet wipe comprising a PVOH  
5 containing binder in contact with an aqueous solution containing borate and bicarbonate ions. The towelette exhibits desirable wet tensile strength but rapid disintegration in water. This material is used as a flushable, dispersible and biodegradable wet wipe for  
10 babies, kids, teens and adults of both male and female of all ages. Applicants' wet wipe can be disposed discreetly by flushing down the toilet bowl safely. The product also meets aerobic and anaerobic biodegradation existing in sewer and septic systems. Applicants' invention further comprises  
15 a mild binder and lotion system that allows the wet wipe to disperse into very small fibrous components under conditions of volumes and velocity of the water in which the wipe is placed.

#### SUMMARY OF THE INVENTION

20 The present invention relates to a pre-moistened, dispersible, and biodegradable wet wipe comprising a non-woven web of fibers contacted with a PVOH containing binder. The binder can be either a polyvinyl alcohol, an aqueous polyvinyl alcohol stabilized polymer emulsion, a blend of a  
25 polyvinyl alcohol or an aqueous polymer emulsion or a combination thereof. The binder-contacted web further comprises an aqueous lotion solution comprising from about 0.1 to about 0.9 percent by weight of the lotion of boric acid and from about 5 to about 8 percent by weight of the  
30 lotion of an alkali metal bicarbonate. The resulting wet wipe has a pH between 7 and about 9 and a wet strength between about 8 and about 20 oz/in.

The present invention relates to a pre-moistened, dispersible, and biodegradable wet wipe comprising a non-  
35 woven web of fibers contacted with a PVOH containing binder. The binder can be either a polyvinyl alcohol, an aqueous

polyvinyl alcohol stabilized polymer emulsion, a blend of a polyvinyl alcohol or an aqueous polymer emulsion or a combination thereof. The wet wipe also comprises an aqueous lotion solution comprising from about 0.3 to about 0.7 percent by weight of the lotion of boric acid and from about 6 to about 7 percent by weight of the lotion of sodium bicarbonate, and further comprising propylene glycol, cocoamphodiacetate, polysorbate 20, methyl paraben, propyl paraben, and Suttocide A. The resulting wet wipe has a pH between 7 and about 9 and a wet strength between about 12 and about 16 oz/in.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 depicts cross-directional lotionized tensile (CDLT) values vs. time over one month at room temperature for wet wipes comprising lotion compositions 1-12 having various boric acid/sodium bicarbonate concentrations. The lotion compositions are shown in Table 1.

Figure 2 depicts CDLT values vs. time over one week at 52°C for wet wipes comprising lotion compositions 7-12 having various boric acid/sodium bicarbonate concentrations. The lotion compositions are shown in Table 1.

Figure 3 depicts CDLT values vs. time over one week at room temperature for wet wipes comprising lotion compositions 13-20 having various boric acid/sodium bicarbonate concentrations. The lotion compositions are as follows (% boric acid/% sodium bicarbonate): 13 = 0.99%/5.5%; 14 = 0.99%/6.5%; 15 = 0.66%/5.5%; 16 = 0.66%/6.5%; 17 = 0.33%/5.5%; 18 = 0.33%/6.5%; 19 = 0.11%/5.5%; and 20 = 0.11%/6.5%.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention relates to a non-woven wet wipe product that is both safe to use and also flushes and disperses and finally biodegrades in the appropriate

environments. This material is used as a flushable, dispersible and biodegradable wet wipe for both male and female babies, kids, teens and adults of all ages. The wet wipe of the invention has an alkaline pH but yet retains mildness and gentleness allowing its use in applications for children and infants.

As used herein, the term "wet wipe" is meant to refer to a non-woven web of fibers that can be used for cleansing purposes. The wet wipe can also be referred to as a towelette.

As used herein, the term "dispersible" is meant to refer to the breaking apart of the wet wipe in water or other liquid solutions.

As used herein, the term "percent by weight" is meant to refer to the quantity by weight of a compound in the lotion of the wet wipe as a percentage of the weight of the lotion.

In its basic form, the wet wipe of the invention consists of a non-woven fibrous material, bonded with a PVOH system and lotionized with a non-irritating formula containing very low levels of boric acid and a moderate level of sodium bicarbonate. The wet wipe is composed primarily of cellulose wood pulp fibers with an added amount of textile fibers to enhance wet and dry strength. It is preferred that the wood pulp fibers comprise about 75% to about 95% and the textile fibers comprise about 5% to about 25% of the wet wipe. It is more preferable that the wood pulp fibers comprise about 85% to about 90% and the textile fibers comprise about 10% to about 15% of the wet wipe. The preferred textile fibers include rayon, cotton, wool, acetate or tencel fibers.

The art skilled will readily have the knowledge necessary to procure a web of fibers capable of being used as a wet wipe. Those skilled in the art of non-woven materials will readily appreciate that a web of fibers can be formed by carding, by wet laying, by spunbonding, as well as by melt blowing. Moreover, these processes can be



combined to achieve unique results. The homogeneous air laid structure that is preferred offers the most desirable and economical version for this application.

The non-woven web of the wet wipe is formed preferably by the airlaid process, where all fibers are intimately blended rather than layered, to achieve a high degree of blend homogeneity as well as high specific volume. The airlaid web is compressed and can be embossed with a pattern. Embossing can produce wet wipe products having a variety of words, pictures, or the like, such as, for example, animals, dollshapes, and the like. The airlaid web is sprayed on both sides with a PVOH binder so that a low level of solids add-on of about 2% to about 20% is applied. It is preferred that a solids add-on of about 5% to about 10% is applied. The binder is typically in a 30% solids solution, preblended, and ready to dilute to a 10% solution which can be applied at about 100% wet pick up, to get a 10% binder add-on.

The web is air dried and wound on a roll. The web is slit, folded, pre-moistened with lotion, cut and stacked into a tub. The lotion saturation is about 100% to about 350% saturation. It is more preferable that the lotion saturation is about 250% to about 350% saturation. The basis weight of the web (dry weight) is about 70 grams/square meter. The wet thickness of the product is about 20 to about 25 mils (1 mil = 1/1000 of an inch). Existing wet wipe products include Kid Fresh and Sofkins.

The PVOH containing binders of the present invention include PVOH, an aqueous PVOH stabilized polymer emulsion, a blend of a PVOH and an aqueous polymer emulsion or a combination thereof. The preferred binder is the Air Products A-911 PVOH binder.

The lotion formulation comprises water, a low level of boric acid, preferably from about 0.1 to about 0.9 percent by weight of the lotion, and a moderate level of an alkali metal bicarbonate, preferably from about 5 to about 8 percent by weight of the lotion, making it a very gentle

lotion. The lotion more preferably comprises from about 0.3 to about 0.7 percent by weight of the lotion of boric acid and from about 6 to about 7 percent by weight of the lotion of an alkali metal bicarbonate. The alkali metal bicarbonate is preferably sodium bicarbonate. The boric acid and sodium bicarbonate are mixed in the lotion solution, rather than in the binder mix.

The lotion formulation also comprises a preservative system. Current commercial preservative systems are designed for acidic wet wipes. Therefore, an alkaline lotion formulation comprising a preservative system provides several advantages including protection against microorganisms and long-term storage. It is preferred that the preservative provide anti-microbial activity including anti-bacterial activity, anti-fungal activity or anti-yeast activity, or a combination thereof. It is also preferred that the preservative provide the wet wipe of the invention the ability to be stored for as long as three years. Preferred preservatives include formaldehyde and formaldehyde donors, glutaraldehyde, quaternium-15, imidazolidinyl and diazolidinyl urea, parabens, chloroxynol, chlorothymol, triclosan, propamidine isethionate, dibromopropamide, hexaminidine, isethionate, zinc pyrithione, oxadine A, kathon, alkyltrimethylammonium bromide, benzalkonium chloride, bezethonium chloride, piroctone olamine, glycerol monolaurate, or a combination thereof. The preservative generally comprise from about 0.01 to about 1.5 percent by weight of the lotion.

The lotion formulation can also comprise moisturizing and/or emollient agents, surfactants and/or emulsifiers, and fragrances. Preferred moisturizers and emollients include polyols, proteins, plant derivatives, and water soluble barrier forming materials, such as, for example, lanolins, fatty acids, alcohols, and the like, or a combination thereof. The moisturizers and emollients generally comprise from about 0.1 to about 10.0 percent by weight of the lotion. Preferred surfactants and emulsifiers

include primary alkyl sulfates, fatty alkylether sulfates, fatty monoglyceride sulfate, fatty acid peptide condensates, fatty acid-sarcosine condensates, sulfosuccinic acid esters, poly glycosides, phospholipids, linear alkylate sulfonates, and amphoterics, or a combination thereof. The surfactants and emulsifiers generally comprise from about 0.1 to about 10.0 percent by weight of the lotion. Fragrances include those that are currently available on the market which are chemically compatible with the lotion formulation. The fragrances generally comprise from about 0.01 to about 2.0 percent by weight of the lotion. A preferred lotion is the Baby Fresh base lotion. It is preferred that the pH of the lotion system be between about 7 and about 9 for use with babies and infants.

For an individual to use the wet wipe without its disintegration in the individual's hand, the wet wipe of the invention must have a sufficient wet strength. The wet strength of the wet wipe can be evaluated by the well known CDLT strength test described in Example 2. The wet wipe wet strength is preferably examined in an aging test at 1 week, 1 month, and 3 months. An acceptable wet wipe possesses a wet strength that has passed a room temperature and 50°C aged test. After aging in room temperature and 50°C, the wet wipe preferably retains significant cross-directional wet strengths of 8 to 20 oz/in. More preferably, the wet wipe retains cross-directional wet strengths of 12 to 16 oz/in. A typical wet wipe CDLT test is presented in Example 3 herein.

Appropriately sized, the wet wipe is also flushable in normal household toilet systems. The wet wipe of the invention readily disintegrates with agitation in a large volume of water. To analyze dispersibility, which is a measure of flushability, the snag breakup test is preferred. A dispersibility time of less than three minutes is preferred. It is more preferred that the dispersibility time is less than two minutes.

The wet wipes of the present invention are preferably biodegradable. The wet wipes will also be mild such that they can be used for human use without inducing allergic responses or other similar phenomena. The wet  
5 wipes preferably pass the repeated insult patch test (RIPT) and other toxicity testing. The wet wipes of the invention are non-toxic to humans.

It is surprising to find a total lotion system that meets the balanced requirements of mildness and  
10 strength while retaining the ability to be dispersible. The present invention provides an alkaline wet wipe comprising a gentle lotion system containing low concentrations of boric acid and relatively high levels of sodium bicarbonate, while  
15 maintaining strength and dispersibility. This combination of properties is highly desirable.

#### EXAMPLES

##### Example 1: The Snag Breakup Test

The snag breakup test can be used to determine the time required to breakup a single wet wipe product.  
20 Generally, a stir bar is placed in a beaker that is filled to a depth of six inches with water or a buffer of appropriate pH. The beaker is placed on a magnetic stirrer and the speed is adjusted as desired. The solution is adjusted to the desired testing temperature. The wet wipe  
25 sample for testing is wrapped around a steel rod, that is preferably 8 inches long, 1/8 inch in diameter, with a hooked end (about 1/4 inch bent at an angle of 110°). The sample preferably does not extend beyond the bent end of the rod. The solution is stirred at a constant velocity and the  
30 rod is placed in a clamp attached to a ring stand. The rod is located above the beaker at a point midway between the center and the rim of the beaker. The sample is gently lowered into the solution until the sample is fully submerged. The time is measured until the first piece of  
35 any size breaks away from the wet wipe and until the sample breaks free from the steel rod.

**Example 2: CDLT Test**

The wet strength of wet wipes of varying concentrations of boric acid and sodium bicarbonate were examined by CDLT at room temperature and the results presented in Table 1. The CDLT of a sample wet wipe is preferably tested on an appropriate apparatus such as the Thwing-Albert Intelect II STD Apparatus according to instructions set forth by the manufacturer. The test procedures for determining dry tencel strength of a sample wet wipe are well known by the art skilled and are briefly set forth herein. Five sample strips are placed squarely in the top clamp of the tencel strength apparatus. The clamps are closed and one of the strips hanging from the top clamp is separated and its free end is placed in the bottom clamp. A very light tension is applied to remove the slack and the bottom clamp is applied. The test is then begun according to the instructions set forth by the manufacturer. After the test strip fractures, the test sequence is repeated for the four remaining sample strips. For wet tencel strength, five sample strips are tested. The two ends of the sample strip are placed together to form a loop in the center. The bent loop portion of the sample is placed into the beaker of either distilled water to test unlotionized wet wipes or into a beaker containing the lotion to test lotionized wet wipes. The wet center loop of the sample is gently touched to a towel to remove excess water or lotion and the sample is then inserted into the grips of the apparatus. The dry tencel strength sequence is then performed. As can be seen from Table 1, satisfactory CDLT with very low levels of boric acid concentrations can be achieved. Figures 1 and 2 show CDLT values for solutions 1-12 over one month at room temperature (21°C) and at 52°C, respectively. In addition, the variation of boric acid with bicarbonate is depicted in Figure 3. Moreover, Table 2 presents wet strength values for wet wipes having various lotion compositions after one week at room temperature. As can be seen, significant strength can be achieved with wet wipes having lotion

concentrations of boric acid as low as 0.33% when the sodium bicarbonate concentrations are raised.

Table 1

CDLT at Various Concentrations and Aging (oz./in.)

5	Soln.	Solution	1	7/8	2	4	pH	1 wk
	52°C No.	Borate/bicarb/H <sub>2</sub> O	Day	Days	Wks	Wks		
	1	0.99%/1.5%/W	5.9	4.4	X	X	7.72	X
	2	0.66%/1.5%/W	6.1	4.6	X	X	7.85	X
10	3	0.33%/1.5%/W	6.9	3.7	X	X	8.33	X
	4	0.99%/4.5%/W	10.7	7.6	7.9	7.9	8.05	X
	5	0.66%/4.5%/W	10.3	8.5	8.6	7.9	8.02	X
	6	0.33%/4.5%/W	9.7	7.9	7.0	6.3	8.16	X
	7	0.99%/7.5%/W	14.6	13.3	13.0	11.5	8.06	
15	8.5							
	8	0.66%/7.5%/W	13.6	12.2	12.3	11.9	8.14	
	6.8							
	9	0.33%/7.5%/W	10.7	10.2	10.1	10.3	8.14	
20	6.4							
	10	0.9%/10%/W	15.5	15.0	14.6	11.4	7.77	
	11.8							
	11	0.99%/7.5%/L	15.8	15.2	13.2	10.8	7.83	
25	8.1							
	12	0.9%/7.5%/L	16.1	14.7	13.1	10.4	7.81	
	10.4							

W = H<sub>2</sub>O; L = Baby Fresh Lotion

Table 2

CDLT at 7 Days at Room Temperature (oz./in.)

30	Sodium Bicarbonate %					
	Boric Acid %	1.5	4.5	5.5	6.5	7.5
35	0.11	NA	NA	5.7	5.4	NA
	0.33	3.7	7.9	6.5	8.4	10.2
	0.66	4.6	8.5	10.1	9.9	12.2
	0.99	4.4	7.6	10.9	12.8	13.3

**Example 3: Compositions of Lotion for Wet Wipes**

The following lotion solutions are preferred.

**0.5% Solution**

	Water.....	91.22%
5	Propylene Glycol.....	1.50%
	Cocoamphodiacetate.....	0.25%
	Polysorbate 20.....	0.20%
	Methyl Paraben.....	0.20%
	Propyl Paraben.....	0.03%
10	Sodium bicarbonate.....	6.00%
	Boric acid.....	0.50%
	Suttocide A.....	0.1%

**0.6% Solution**

	Water.....	91.12%
15	Propylene Glycol.....	1.50%
	Cocoamphodiacetate.....	0.25%
	Polysorbate 20.....	0.20%
	Methyl Paraben.....	0.20%
	Propyl Paraben.....	0.03%
20	Sodium bicarbonate.....	6.00%
	Boric acid.....	0.60%
	Suttocide A.....	0.1%

**0.7% Solution**

	Water.....	91.02%
25	Propylene Glycol.....	1.50%
	Cocoamphodiacetate.....	0.25%
	Polysorbate 20.....	0.20%
	Methyl Paraben.....	0.20%
	Propyl Paraben.....	0.03%
30	Sodium bicarbonate.....	6.00%
	Boric acid.....	0.70%
	Suttocide A.....	0.1%



**WHAT IS CLAIMED IS:**

1. A pre-moistened, dispersible, biodegradable wet wipe comprising:
  - a) a web of non-woven fibers and a binder  
5 selected from the group consisting of a polyvinyl alcohol, a polymer emulsion stabilized with an aqueous polyvinyl alcohol, a blend of a polyvinyl alcohol and an aqueous polymer emulsion, and a combination thereof;
  - b) an aqueous lotion comprising: from about 0.1  
10 to about 0.9 percent by weight of the lotion of boric acid; from about 5 to about 8 percent by weight of the lotion of an alkali metal bicarbonate; and a preservative effective for inhibiting microbial activity in said lotion; and
  - c) said wet wipe having a pH between 7 and about  
15 9 and a wet strength between about 8 and about 20 oz/in.
2. The wet wipe of claim 1 in which the amount of the aqueous lotion solution ranges from 100 to 350 percent by weight of the web.
3. The wet wipe of claim 1 in which the boric  
20 acid is from about 0.3 to about 0.7 percent by weight of the lotion.
4. The wet wipe of claim 1 in which the alkali metal bicarbonate is from about 6 to about 7 percent by weight of the lotion.

- 16 -

5. The wet wipe of claim 1 in which the boric acid is from about 0.3 to about 0.7 percent by weight of the lotion and the alkali metal bicarbonate is from about 6 to about 7 percent by weight of the solution.

5 6. The wet wipe of claim 5 in which the wet wipe has a wet strength between about 12 and about 16 oz/in.

7. The wet wipe of claim 1 in which the alkali metal bicarbonate is sodium bicarbonate.

8. The wet wipe of claim 1 wherein the aqueous  
10 lotion solution further comprises a moisturizer and a surfactant.

9. The wet wipe of claim 8, wherein the aqueous solution further comprises a fragrance.

10. A pre-moistened, dispersible, biodegradable  
15 wet wipe comprising:

a) a web of non-woven fibers and a binder selected from the group consisting of a polyvinyl alcohol, a polymer emulsion stabilized with an aqueous polyvinyl alcohol, a blend of a polyvinyl alcohol and an aqueous  
20 polymer emulsion, and a combination thereof;

b) an aqueous lotion comprising: from about 0.3 to about 0.7 percent by weight of the lotion of boric acid;

from about 6 to about 7 percent by weight of the lotion of sodium bicarbonate;

c) said lotion further comprising: propylene glycol, cocoamphodiacetate, polysorbate 20, methyl paraben, 5 propyl paraben, and Suttocide A, which is effective for inhibiting microbial activity in said lotion; and

d) said wet wipe having a pH between 7 and about 9 and a wet strength between about 8 and about 20 oz/in.

1/3




FIG.1

2/3




FIG. 2




FIG. 3

# INTERNATIONAL SEARCH REPORT

Internat'l Application No

PCT/US 96/02639

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 D04H1/64

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 D04H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,5 252 332 (GOLDSTEIN JOEL E) 12 October 1993 see column 2, line 20 - column 3, line 61 ---	1,8-10
A	PATENT ABSTRACTS OF JAPAN vol. 018, no. 647 (C-1283), 8 December 1994 & JP,A,06 248548 (KURARAY CO LTD), 6 September 1994, see abstract ---	1,10
A	US,A,3 689 314 (DUCHANE DAVID V) 5 September 1972 cited in the application see column 3, line 3 - column 6, line 69 --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

5 August 1996

Date of mailing of the international search report

16. 08. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

V Beurden-Hopkins, S

# INTERNATIONAL SEARCH REPORT

Internal . Application No  
PCT/US 96/02639

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,3 808 165 (DUCHANE D) 30 April 1974 cited in the application see column 5, line 19 - column 6, line 8 ---	1
A	EP,A,0 003 186 (AIR PROD & CHEM) 25 July 1979 see page 2, line 10 - page 5, line 2 -----	1



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/02639

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5252332	12-10-93	AT-T- 131228 CA-A- 2100814 DE-D- 69300949 DE-T- 69300949 EP-A- 0582123 JP-A- 6198778	15-12-95 25-01-94 18-01-96 25-04-96 09-02-94 19-07-94
US-A-3689314	05-09-72	CA-A- 944107 DE-A- 2109554 FR-A- 2080735 GB-A- 1315465	26-03-74 09-09-71 19-11-71 02-05-73
US-A-3808165	30-04-74	AU-B- 461173 AU-B- 5939573 CA-A- 1012667 DE-A- 2341815 FR-A,B 2197056 GB-A- 1446782 JP-A- 49057162 NL-A- 7311442	15-05-75 20-02-75 21-06-77 07-03-74 22-03-74 18-08-76 03-06-74 25-02-74
EP-A-0003186	25-07-79	US-A- 4245744 US-A- 4258849 CA-A- 1104026 JP-A- 54104962 US-A- 4343403 US-A- 4343133 CA-A- 1109758 JP-A- 54104963 US-A- 4372447 US-A- 4343134	20-01-81 31-03-81 30-06-81 17-08-79 10-08-82 10-08-82 29-09-81 17-08-79 08-02-83 10-08-82